

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2018

Classification no.	2026-Efectis-R000677
Sponsor	AKOpanel De Singel 26 7722 RR DALFSEN THE NETHERLANDS
Product name	PETpanel 18 mm
Prepared by	Efectis Nederland BV
Author(s)	Nina Brouwer Job Onderwater
Project number	ENL-25-001374
Date of issue	May 2026
Number of pages	5

1. INTRODUCTION

This classification report defines the classification assigned to **PETpanel 18 mm** in accordance with the procedures given in EN 13501-1:2018.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **PETpanel 18 mm**, is defined as wall and ceiling covering.

2.2 MANUFACTURER

AKOpanel
De Singel 26
7722 RR DALFSEN
THE NETHERLANDS

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is composed of:

- 60% recycled PET
- 40% new PET

In the colour Black 09.

The panels were mounted mechanically on 40 mm AKOpanel reinforcement rails.

The product has a total thickness of 18 +/- 0.5 mm, a density of approx. 140 kg/m³ and a mass per unit area of approx. 2.5 kg/m².

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2020	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2020+A1:2022	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13238:2010	Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates
EN 13501-1:2018	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	AKOpanel THE NETHERLANDS	2026-Efectis-R000675 2026-Efectis-R000676	EN ISO 11925-2:2020 EN 13823:2020+A1:2022

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Surface flame impingement	Fs ≤150 mm	6	45	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	35	-
	Ignition of filter paper		-	Compliant

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	13	-
	FIGRA _{0.4MJ} [W/s]		13	-
	THR _{600s} [MJ]		1.2	-
	LFS < edge		-	Compliant
	SMOGRA [m²/s²]		1.1	-
	TSP _{600s} [m²]		27	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class Test method(s)	B	C	D
EN ISO 11925-2 Exposure = 30 s	$F_s \leq 150$ mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	$FIGRA_{0.2\text{ MJ}} \leq 120$ W/s LFS < edge of specimen $THR_{600s} \leq 7.5$ MJ	$FIGRA_{0.4\text{ MJ}} \leq 250$ W/s LFS < edge of specimen $THR_{600s} \leq 15$ MJ	$FIGRA_{0.4\text{ MJ}} \leq 750$ W/s
Additional classification			
Smoke production	s1 = $SMOGRA \leq 30$ m ² /s ² and $TSP_{600s} \leq 50$ m ² ; s2 = $SMOGRA \leq 180$ m ² /s ² and $TSP_{600s} \leq 200$ m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2 CLASSIFICATION

The product, **PETpanel 18 mm**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

4.3.1 Direct field of application

This classification is valid for the following product parameters:

Thickness	18 +/- 0.5 mm
Mass per unit area	2.5 kg/m ²
Density	140 kg/m ³
Colour	Black 09

This classification is valid for the following end use applications:

Substrate	Non-combustible (class A1/A2, 870 ± 50 kg/m ³ , according to EN 13238:2010) Standard substrates density > 75% nominal density
Application	Free standing
Air gap	Yes, ≥ 80 mm
Methods and means of fixing	Mechanically with AKOpanel reinforcement rails system.
Joints	Vertical and horizontal
Other aspects of end use conditions	Closed surface, no openings or gaps between components

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

Consult classification standard and national laws and regulations for limitations on the period of validity of the classification.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.



Signed by: Nina BROUWER

Project Leader Reaction to Fire



Signed by: Job ONDERWATER

Project Leader Reaction to Fire